

RX75FA

Application: POS receipts, ATM receipts


Description:

- standard sensitivity
- 10 years durability at correct storage for thermal paper
- improved stability against environmental influences
- bisphenol A (BPA) free


Physical Properties	Value	Test Method
Substance 17 x 22 - 500 sheets	75 g/m ² ± 4 g/m ² 19.9 ± 1.1#	ISO 536
Caliper	82 ± 5 µm 3.23 ± 0.20 mils	ISO 534
Smoothness (Bekk, front)	≥ 300 s	ISO 5627
Brightness (front)	≥ 80 %	ISO 2470
Tensile strength MD	≥ 60 N / 15 mm	ISO 1924-2
CD	≥ 30 N / 15 mm	ISO 1924-2
Preservation Properties	Optical density after ageing *	Conditions
Heat resistance	≥ 90 %	24h / 50°C
Moisture resistance	≥ 80 %	24h / 40°C 80% RH
Light resistance	≥ 75 %	24h / 16.000 lux

* based on maximum optical density

Dynamic Sensitivity



Static Sensivity



subject to change without notice
Revision: 3 / last update 10.21